CERTIFIED MATERIAL TEST REPORT

GERDAU

US-ML-PETERSBURG
25801 HOFHEIMER WAY
PETERSBURG, VA 23803-8905
USA

GRADE	SHAPE / SIZE	DOCUMENT ID:
A992/A572-50	Wide Flange Beam / 12 X 65# / 310 X 97	0000464512

LENGTH	PCS	WEIGHT	HEAT / BATCH
40' 00"	16	41,600 LB	**60144159**/03

SALES ORDER	CUSTOMER MATERIAL Nº
13185218/000010	000000003712650040

SPECIFICATION / DATE or REVISION
ASTM A6-17
ASTM A709-21 GR50
ASTM A992-20, A572-21
CSA G40.21-13 345WM, 50W

CUSTOMER PURCHASE ORDER NUMBER	BILL OF LADING	DATE
G450041721	1330-0000200857	07/25/2023

CHEMICAL COMPOSITION

C (%)	Mn (%)	P (%)	S (%)	Si (%)	Cu (%)	Ni (%)	Cr (%)	Mo(%)	Sn (%)	V (%)	Nb (%)	Al (%)	CEqvA6 (%)
0.09	1.08	0.012	0.033	0.24	0.37	0.18	0.18	0.040	0.012	0.001	0.013	0.003	0.35

MECHANICAL PROPERTIES

YS 0.2% (PSI)	UTS (PSI)	YS (MPa)	UTS (MPa)	Y/T rati (%)	G/L (Inches)	G/L (mm)	Elong. (%)
54966	72060	379	497	0.760	8.000	200.0	26.20
52915	69986	365	483	0.760	8.000	200.0	26.70

COMMENTS / NOTES

Gerdau's steel is 100% recyclable. Support the circular economy through our Metals Recycling Partnership. For details, visit www2.gerdau.com/metals-recycling, or contact metalsrecycling@gerdau.com.

The above figures are certified chemical and physical test records as contained in the permanent records of the company. We certify that these data are correct and in compliance with specified requirements. No weld repair was performed on this material. The material has not been in contact with mercury while in Gerdau possession. For all products other than billets or beam blanks, this material was produced (Electric Arc Furnace, Melted, Continuously Cast, Hot Rolled and, if applicable, Cold-Drawn) in the USA. For billets or beam blanks, this material was produced (Electric Arc Furnace, Melted and Continuously Cast) in the USA. CMTR complies with EN 10204 3.1.

BHASKAR YALAMANCHILI
QUALITY DIRECTOR
Phone: (409) 267-1071 Email: Bhaskar.Yalamanchili@gerdau.com

ALICE PITCHFORD
QUALITY ASSURANCE MGR.
Phone: (804) 524-2851 Email: Alice.pitchford@gerdau.com