

Customer PO	4500559291	Sales Order #	11064274 - 8.1
Product Group	Hot Roll - Merchant Bar Quality	Product #	3006263
Grade	Nucor Multigrade	Lot #	110005040363
Size	3.5" x 3.5" x 0.375"	Heat #	1100050403
BOL #	BOL-1544426	Load #	1497342
Description	Hot Roll - Merchant Bar Quality Equal Angle 3 1/2" x 3 1/2" x 3/8" Nucor Multigrade 20' 0" [240"] 2001-6000 lbs	Customer Part #	503163161220
Production Date	09/05/2023	Qty Shipped LBS	5100
Product Country Of Origin	United States	Qty Shipped EA	30
Original Item Description		Original Item Number	

I hereby certify that the material described herein has been manufactured in accordance with the specifications and standards listed above and that it satisfies those requirements.

Melt Country of Origin : United States

Melting Date: 08/20/2023

C (%)	Mn (%)	P (%)	S (%)	Si (%)	Ni (%)	Cr (%)	Mo (%)	Cu (%)	Ti (%)	V (%)	Nb (%)
0.14	0.89	0.017	0.006	0.223	0.15	0.28	0.04	0.28	0.001	0.039	0.002

Sn (%)

0.009

ASTM A529 S78.2 CE (%) : 0.42

Tensile testing

	Yield (PSI)	Tensile (PSI)	Elongation in 8" (%)
(1)	58100	75600	22.0
(2)	58600	75900	21.0

Comments:

NUCOR MULTIGRADE MEETS THE REQUIREMENTS OF: ASTM A36/A36M-14; A529/529M-05(2009) GR50(345); A572/572M-07 GR50(345); A709/709M-10 GR36(250) & GR50(345); CSA G40.21-04 GR44W(300W) & GR50W(350W); AASHTO M270/M270M-10 GR36(270) & GR50(345); ASME SA36/SA36M-07; MEETS REPORTING REQUIREMENTS OF EN10204 SEC 3.1

1. All manufacturing processes of the steel, including melting, casting & hot rolling, have been performed in U.S.A
2. Mercury not intentionally added at any point during manufacturing or testing of this material.
3. Welding or weld repair was not performed on this material.
4. This material conforms to the specifications described on this document and may not be reproduced, except in full, without written approval of Nucor Corporation.
5. Results reported ASTM E45 (Inclusion content) and ASTM E381 (Macro-etch) are provided as interpretation of ASTM procedures.

