

US-ML-MIDLOTHIAN

300 WARD ROAD MIDLOTHIAN, TX 76065 USA

WEIGHT PCS LENGTH A STREET PRODUCTION OF THE MANHATTAN,KS 66505-1688 9,120 LB LONGVIEW,TX 75604-4817 40'00" USA USA SPECIFICATION / DATE or REVISION CUSTOMER MATERIAL Nº SALES ORDER ASTM A6-17 000000003716570040 ASTM A709-21 GR50 13548119/000010 ASTM A992-20, A572-21 DATE CSA G40.21-13 345WM, 50W BILL OF LADING

GRADE

A992/A572-50

CUSTOMER PURCHASE ORDER NUMBER 11/22/2023 1327-0000556381 4500563660 CEqvA6 (%) A) (%) Nb (%) V (%) Sn (%) Mo(%) CHEMICAL COMPOSITION C (%) Mn (%) Cr (%) Ni (%) Cu (%) Si (%) 0.34 S (%) 0.003 P (%) 0.021 0.004 0.011 0.050 0.17 0.17 0.30 0.20 0.036 0.016 0.07 0.10

CERTIFIED MATERIAL TEST REPORT

CUSTOMER BILL TO

C (%) Mn (%) 0.10 0.97	0.016 0.036	0.20 0.30	0.17 0.17	0.050 0.011 0.004	G/L (Inches)	G/L (mm)	Elong. (%) 24.50
MECHANICAL PROPERTIES YS 0.2% (PSI) 55281 56923	UTS (PSI) 73688 76754	YS (MPa) 381 393	UTS (MPa) 508 529	Y/T rati (%) 0.750 0.740	8,000 8.000	200.0 200.0	24.50

COMMENTS / NOTES

Gerdau's steel is 100% recyclable. Support the circular economy through our Metals Recycling Partnership. For details, visit www2.gerdau.com/metals-recycling, or contact metalsrecycling@gerdau.com.

The above figures are certified chemical and physical test records as contained in the permanent records of the company. We certify that these data are correct and in compliance with specified requirements. No weld repair was performed on this material. The material has not been in contact with mercury while in Gerdau possession. For all products other than billets or beam blanks, this material was produced (Electric Arc Furnace, Melted, Continuously Cast, Hot Rolled and, if applicable, Cold-Drawn) in the USA. For billets or beam blanks, this material was produced (Electric Arc Furnace, Melted and Continuously Cast) in the USA. CMTR complies with EN 10204 3.1.

Mackey BHASKAR YALAMANCHILI
QUALITY DIRECTOR

Phone: (409) 267-1071 Email: Bhaskar. Yalamanchili@gerdau.com

Wale A. FL WADE LUMPKINS

SHAPE / SIZE

X 85

Wide Flange Beam / 16 X 57# / 410

Page 1 / 1

0001029392

HEAT / BATCH

60146282/02

DOCUMENT ID:

Phone: 972-779-3118 Email: Wade.Lumpkins@gerdau.com