

CMC STEEL ALABAMA 101 S 50TH STREET BIRMINGHAM AL 35212-3525

CERTIFIED MILL TEST REPORT For additional copies call 800-227-6489

We hereby certify that the test results presented here are accurate and conform to the reported grade specification

Marcus W. McCluney - CMC Steel AL

Quality Assurance Manager

1SERIES-BPS®

HEAT NO.:1089843

SECTION: ANG 5 X 3x5/16 40'0" A36/52950

GRADE: ASTM A36-19/A529-19 Gr 50

ROLL DATE: 11/27/2023 MELT DATE: 11/10/2023

Cert. No.: 85690585 / 089843B195

Delivery#: 85690585 BOL#: 75794257

CUST PO#: 4500568065 CUST P/N: 505003001040

DLVRY LBS / HEAT: 9840.000 LB DLVRY PCS / HEAT: 30 EA

Characteristic	Value	Characteristic	Value	Characteristic Value
С	0.16%	Elongation Gage Lgth test 1	8IN	
Mn	0.64%	Yield to tensile ratio test1	0.73	
P	0.009%	Yield Strength test 2	54.1ksi	
S	0.022%	Tensile Strength test 2	75.2ksi	
Si	0.17%	Elongation test 2	25%	
Cu	0.36%	Elongation Gage Lgth test 2	8IN	
Cr	0.16%	Yield to tensile ratio test2	0.72	
Ni	0.14%			
Мо	0.043%			The Following is true of the material represented by this MTR:
V	0.004%			*Material is fully killed and is Hot Rolled Steel
Cb	0.009%			*100% melted, rolled, and manufactured in the USA
Sn	0.011%			*EN10204:2004 3.1 compliant
В	0.0002%			*Contains no weld repair
Ti	0.001%			*Contains no Mercury contamination
N	0.0083%			*Manufactured in accordance with the latest version
Carbon Eq A6	0.34%			of the plant quality manual
Carbon Eq A529	0.37%			*Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661
Yield Strength test 1	54.4ksi			*Warning: This product can expose you to chemicals which are
Tensile Strength test 1	74.6ksi			known to the State of California to cause cancer, birth defects
Elongation test 1	27%			or other reproductive harm. For more information go
				to www.P65Wamings.ca.gov

REMARKS : ALSO MEETS ASTM GRADE A36 REV 08, A572-21 GR 50, A709-36, A709-50, A992, AASHTO GRADE M270-36, M270-50, CSA G40.21-04 GRADE 44W, 50W, ASME SA-36 2008A ADDEND A.