

Atlas Tube Corp. Chicago
 1855 East 122nd Street
 Chicago Illinois USA
 60633
 Tel: 773-646-4500
 Fax: 773-646-6128



REF./L: 81193913
 Date: 01/03/2024
 Customer: 1746

MATERIAL TEST REPORT

Sold To: HOUSTON TX 77213 USA

Shipped To: HOUSTON TX 77029 USA
 Service Co:

Material: 3.0x3.0x375x52.0°0(6x1)PB

Material No: 30030375

Made in: USA

Sales Order: 1993848

Purchase Order: SSW140098

Melted and Poured in: USA

Heat No	C	Mn	P	S	Si	Al	Cu	Co	Mo	Ni	Cr	V	Ti	B	N	Ca								
W66013G23	0.210	0.810	0.013	0.009	0.015	0.042	0.030	0.005	0.005	0.010	0.050	0.002	0.001	0.0001	0.0040	0.0000								
Bundle No	PCs		Yield	Tensile		Eln.2in		Certification																
M801173456	6		061341 Psi	074342 Psi		34.0 %		ASTM A500-21 GRADE B&C																
Heat	MILL			MILL Location			Method			Recycled Content			Post Consumer			Pre-Consumer (Post Industrial)			% Harvested			Within Miles of Location		
W66013G23USSSTEEL	GARY,IN			BOF			34.20%			19.80%			14.40%			100%			500					

Material Note:

Date: 2/22/2024 To: SENTRY SUPPLY dba SO#: A806807 L#: 2 PO#: PO247282 Part: T0400303720 Qty: 1 Heat#: D64036G23* Tag: B08022124 Page: 1 of 5

Material: 8.0x2.0x250x40°0°0(2x2)PB

Material No: 80020250

Made in: USA

Sales Order: 1979421

Purchase Order: SSW139830

Melted and Poured in: USA

Heat No	C	Mn	P	S	Si	Al	Cu	Co	Mo	Ni	Cr	V	Ti	B	N	Ca								
M67293	0.180	0.770	0.012	0.005	0.015	0.033	0.030	0.008	0.006	0.010	0.030	0.001	0.001	0.0001	0.0000	0.0000								
Bundle No	PCs		Yield	Tensile		Eln.2in		Certification																
M801164659	4		061546 Psi	075991 Psi		32.8 %		ASTM A500-21 GRADE B&C																
Heat	MILL			MILL Location			Method			Recycled Content			Post Consumer			Pre-Consumer (Post Industrial)			% Harvested			Within Miles of Location		
M67293 USSSTEEL	GARY,IN			BOF			34.20%			19.80%			14.40%			100%			500					

Material Note:

Authorized by Quality Assurance: *Jason Richard*
Jason Richard

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AV D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type 3.1



Atlas Tube Corp. Chicago
 1855 East 122nd Street
 Chicago Illinois USA
 60633
 Tel: 773-646-4500
 Fax: 773-646-6128



REF B/L: 81193913
 Date: 01/03/2024
 Customer: 1746

MATERIAL TEST REPORT

Sold To:
 HOUSTON TX 77213
 USA

Shipped To:
 8415 Clinton Drive
 HOUSTON TX 77029
 USA

Material: 4.0x3.0x375x40"0"(4x3).

Material No: 400303754000

Made in: USA
 Melted and Poured in: USA

Sales Order: 1994265

Purchase Order: SSW140098

Heat No	C	Mn	P	S	Si	Al	Cu	Ch	Mo	Ni	Cr	V	Ti	B	N	Ca
D64036G23	0.200	0.770	0.014	0.008	0.007	0.039	0.030	0.007	0.005	0.010	0.040	0.001	0.001	0.0001	0.0050	0.0000
Bundle No	PCs	Yield	Tensile	Eln.2in	Certification											
M801173186	12	067186 Psi	084930 Psi	33.9 %	ASTM A500-21 GRADE B&C											
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location								
D64036G23	USSTEEL	GARY,IN	BOF	34.20%	19.80%	14.40%	100%	500								

Material Note:

Material: 4.0x4.0x500x40"0"(4x2).

Material No: 400405004000

Made in: USA
 Melted and Poured in: USA

Sales Order: 1993649

Purchase Order: SSW140098

Heat No	C	Mn	P	S	Si	Al	Cu	Ch	Mo	Ni	Cr	V	Ti	B	N	Ca
M67292G23	0.180	0.770	0.016	0.005	0.016	0.048	0.070	0.006	0.010	0.010	0.040	0.001	0.001	0.0001	0.0050	0.0000
Bundle No	PCs	Yield	Tensile	Eln.2in	Certification											
M801172097	3	070779 Psi	078681 Psi	34.8 %	ASTM A500-21 GRADE B&C											
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location								
M67292G23	USSTEEL	GARY,IN	BOF	34.20%	19.80%	14.40%	100%	500								

Material Note:

Authorized by Quality Assurance: *Jason Richard*
Jason Richard

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AV D3.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 Type 3.1



Atlas Tube Corp. Chicago
1865 East 122nd Street
Chicago Illinois USA
60633
Tel: 773-646-4500
Fax: 773-646-6128

Atlas Tube
A DIVISION OF ZEKELMAN INDUSTRIES

MATERIAL TEST REPORT

REF B/L: 81193913
Date: 01/03/2024
Customer: 1746

Shipped To

8415 Clinton Drive
HOUSTON TX 77029
USA

HOUSTON TX 77213
USA

Material: 4.0x4.0x500x40"0(4x2).

Material No: 400405004000

Made in: USA
Melted and Poured in: USA

Sales Order: 19936649

Purchase Order: SSW140098

Heat No	C	Mn	P	S	SI	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
M67606G23	0.200	0.730	0.010	0.009	0.011	0.063	0.020	0.008	0.007	0.010	0.030	0.001	0.001	0.0001	0.0050	0.0000

Bundle No	PCs	Yield	Tensile	Elm.2in	Certification
M801172097	5	077722 Psi	084931 Psi	34.9 %	ASTM A500-21 GRADE B&C

Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location
M67606G23	USSTEEL	GARY.IN	BOF	34.20%	19.80%	14.40%	100%	500

Material Note:

Sales Or. Note:

Material: 4.0x4.0x500x40"0(4x2).

Material No: 400405004000

Made in: USA
Melted and Poured in: USA

Sales Order: 19936649

Purchase Order: SSW140098

Heat No	C	Mn	P	S	SI	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
M67292G23	0.180	0.770	0.016	0.005	0.016	0.048	0.070	0.006	0.010	0.010	0.040	0.001	0.001	0.0001	0.0050	0.0000

Bundle No	PCs	Yield	Tensile	Elm.2in	Certification
M801172096	8	070779 Psi	078681 Psi	34.8 %	ASTM A500-21 GRADE B&C

Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location
M67292G23	USSTEEL	GARY.IN	BOF	34.20%	19.80%	14.40%	100%	500

Material Note:

Sales Or. Note:

Authorized by Quality Assurance: *Jason Richard*
Jason Richard

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AV D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type 3.1



Atlas Tube Corp. Chicago
 1855 East 122nd Street
 Chicago Illinois USA
 80633
 Tel: 773-646-4500
 Fax: 773-646-8128



REF BL: 81198846
 Date: 01/26/2024
 Customer: 1746

MATERIAL TEST REPORT

8416 Clinton Drive
 HOUSTON TX 77029
 USA

Sold To:
 2007007
 HOUSTON TX 77213
 USA

Material: 4.0x3.0x375x48"0"014x2). Material No: 400303764800 Made in: USA
 Melted and Poured in: USA

Sales Order: 1995799 Purchase Order: SSW140098

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	TI	B	N	Ca
D64035G23	0.190	0.760	0.019	0.009	0.009	0.051	0.030	0.006	0.009	0.020	0.050	0.001	0.001	0.0001	0.0050	0.0000
Bundle No	PCs	Yield	Tensile	Elm.2in	Certification											
M801180478	8	073232 Psi	084378 Psi	33.8 %	ASTM A500-23 GRADE B&C											
Heat	MILL	MILL Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location								
D64035G23	USSTEEL	GARY,IN	BOF	34.20%	19.80%	14.40%	100%	500								

Material Note: Sales Or. Note: Material No: 500505004000 Made in: USA
 Melted and Poured in: USA

Material: 5.0x5.0x500x40"0"0(4x1). Purchase Order: SSW141029

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	TI	B	N	Ca
T65180G23	0.190	0.760	0.014	0.008	0.009	0.046	0.030	0.008	0.006	0.010	0.060	0.001	0.001	0.0001	0.0050	0.0000
Bundle No	PCs	Yield	Tensile	Elm.2in	Certification											
M801177585	4	070685 Psi	079189 Psi	32.9 %	ASTM A500-23 GRADE B&C											
Heat	MILL	MILL Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location								
T65180G23	USSTEEL	GARY,IN	BOF	34.20%	19.80%	14.40%	100%	500								

Authorized by Quality Assurance: *Jason Richard* Jason Richard
 The results reported on this report represent the actual strengths of the material furnished and indicate full compliance with all applicable specifications and contract requirements. CE calculated using the AV D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type 3.1

