GĐ	GERDAU

CUSTOMER PURCHASE ORDER NUMBER

US-ML-CHARLOTTE 6601 LAKEVIEW ROAD CHARLOTTE, NC 28269 USA

4500579615

Page 1 / 1 CERTIFIED MATERIAL TEST REPORT DOCUMENT ID: SHAPE / SIZE GRADE CUSTOMER BILL TO CUSTOMER SHIP TO 0000187572 Angle / 2X1 1/2X1/4 **GGMULTI** HEAT / BATCH WEIGHT The second second section of the second seco LENGTH MANHATTAN,KS 66505-1688 LONGVIEW,TX 75604-4817 54204278/05 3,047 LB 20'00" USA USA SPECIFICATION / DATE or REVISION CUSTOMER MATERIAL Nº SALES ORDER ASTM A529-19, A572-21E1 000000050200116820 14248612/000020 ASTM A6-24A, A36-19, ASME \$A36 ASTM A709-21, AASHTO M270-20 DATE BILL OF LADING CSA G40.20-13/G40.21-13 (R23) 08/14/2024 1321-0000124227

CHEMICAL COMPOSITION Nb (%) V (%) Mo(%) Cr (%) Ni (%) Cu (%) Si (%) S (%) P (%) Mn (%) C (%) 0.008 0.001 0.050 0.19 0.17 0.30 0.18 0.036 0.012 0.67 0.14 MECHANICAL PROPERTIES Elong. (%) 27.50 28.80 YS (MPa) UTS (MPa) 536 535 YS (PSI) UTS (PSI) G/L (Inches) 391 386 56679 5<u>5961</u> 77800 77603 8.000 8.000

GEOMETRIC CHARACTERISTICS R:R

31.00

COMMENTS / NOTES

This grade meets the requirements for the following grades: ASTM Grades: A36; A529-50; A572-50; A709-36; A709-50 CSA Grades: 44W; 50W

AASHTO Grades: M270-36; M270-50

ASME Grades: SA36

Gerdau's steel is 100% recyclable. Support the circular economy through our Metals Recycling Partnership. For details, visit www2.gerdau.com/metals-recycling, or contact metalsrecycling@gerdau.com.

The above figures are certified chemical and physical test records as contained in the permanent records of the company. We certify that these data are correct and in compliance with specified requirements. No weld repair was performed on this material. The material has not been in contact with mercury while in Gerdau possession. For all products other than billets or beam blanks, this material was produced (Electric Arc Furnace, Melted, Continuously Cast, Hot Rolled and, if applicable, Cold-Drawn) in the USA. For billets or beam blanks, this material was produced (Electric Arc Furnace, Melted and Continuously Cast) in the USA. CMTR complies with EN 10204 3.1.

Mackey BHASKAR YALAMANCHILI
QUALITY DIRECTOR

Phone: (409) 267-1071 Email: Bhaskar. Yalamanchili@gerdau.com

Packel Warren

RACHEL WARREN
QUALITY ASSURANCE MGR.

Phone: (704) 596-0361 EX3039 Email: Rachel.Webster@gerdau.com