

Atlas Tube Arkansas
 6651 E Hwy 137
 Blytheville Arkansas USA
 72315
 Tel:
 Fax:



REF.B/L: 81236199
 Date: 08/22/2024
 Customer: 179

MATERIAL TEST REPORT

Sold To

Shipped To

Material: 12.0x4.0x250x40'0"0(2x4). **Material No:** 1200402504000 **Made in:** USA
Sales Order: 2076413 **Purchase Order:** C452006990 **Melted and Poured in:** USA
Cust Material#: 66120040025040

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
24090432	0.220	0.780	0.019	0.003	0.040	0.031	0.100	0.001	0.014	0.030	0.050	0.002	0.001	0.0002	0.0071	0.0018

Bundle No M500525965 **PCs** 8 **Yield** 058244 Psi **Tensile** 074650 Psi **Eln.2in** 35 % **Certification** ASTM A500-23 GRADE B&C **CE: 0.38**

Heat	MILL	Mill Location	Method	Recycled_Content	Post_Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location
24090432	BIGRIVER	Osceola,AR	EAF	76.00%	95.00%	5.00 %	75%	500

Material Note:
Sales Or. Note:

Authorized by Quality Assurance: *Jason Richard*
Jason Richard

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1. Any tubular steel product noted as "Made in USA" and "Melted and Poured in USA" meets the Build America, Buy America Act.

