

CMC STEEL TEXAS
1 STEEL MILL DRIVE
SEGUIN TX 78155-7510

CERTIFIED MILL TEST REPORT

For additional copies call 800-227-6489

We hereby certify that the test results presented here are accurate and conform to the reported grade specification

Stew Lische

Drew M Fischer

1SERIES-BPS®

HEAT NO.:3133039 SECTION: ANG 2 X 2x3/16 20'0" A36/52950

GRADE: ASTM A36-19/A529-19 Gr 50

ROLL DATE: 09/14/2024 MELT DATE: 08/17/2024

Cert. No.: 86035796 / 133039A111

s	Superior Supply & Steel Co 318 N CITIES SERVICE HWY SULPHUR LA
0	
L	318 N CITIES SERVICE HWY
D	SUI PHUR I A

US 70663-5424 T 3376252300 O 3376258509 S H I P

Superior Supply & Steel Co

318 N CITIES SERVICE HWY
SULPHUR LA

T 3376252300 O 3376258509

US 70663-5424

Delivery#: 86035796

BOL#: 76276167 CUST PO#: P0252657-01

CUCT D/N.

CUST P/N:

Quality Assurance Manager

DLVRY LBS / HEAT: 4685.000 LB DLVRY PCS / HEAT: 96 EA

Characteristic	Value	Characteristic	Value	Characteristic Value
С	0.12%	Elongation test 2	27%	
Mn	0.80%	Elongation Gage Lgth test 2	8IN	
Р	0.010%			
S	0.032%			
Si	0.15%			
Cu	0.34%			
Cr	0.09%			
Ni	0.13%			
Мо	0.029%			The Following is true of the material represented by this MTR:
V	0.000%			*Material is fully killed and is Hot Rolled Steel
Cb	0.011%			*100% melted, rolled, and manufactured in the USA
Sn	0.010%			*EN10204:2004 3.1 compliant *Contains no weld repair
Al	0.002%			*Contains no Mercury contamination
				*Manufactured in accordance with the latest version of the plant quality manual
Yield Strength test 1	55.1ksi			*Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661
Tensile Strength test 1	75.1ksi			*Warning: This product can expose you to chemicals which are
Elongation test 1	27%			known to the State of California to cause cancer, birth defects or other
Elongation Gage Lgth test 1	8IN			reproductive harm. For more information go to www.P65Warnings.ca.gov
Yield Strength test 2	55.9ksi			*THE RECORDING OF FALSE, FICTITIOUS OR FRAUDULENT
Tensile Strength test 2	75.5ksi			STATEMENTS OR ENTRIES ON THIS DOCUMENT MAY BE PUNISHABLE
				AS A FELONY UNDER FEDERAL STATUTE

REMARKS : ALSO MEETS ASTM GRADE A36, A529-50, A572-50, A709-36, A709-50, A992, AASHTO M270-36, M270-50, CSA G40.21-04 44W, 50W ALSO MEETS THE REQUIREMENTS OF ASME SA36